

## SAFETY DATA SHEET

ID# SDS-2101 Issue Date: June 1, 2015 Revised Date: October 30, 2024 Revision No. 003

## Section 1: Identification

**Product Identifier:** Sultron<sup>™</sup> LSG R5100 PPSU and Sultron<sup>™</sup> LSG R5500 PPSU natural and colors

## Manufacturer:

Mitsubishi Chemical Advanced Materials, Inc. 2120 Fairmont Ave. Reading, PA 19605 (610) 320-6600

In case of an emergency, please call Chemtrec 1-800-424-9300.

**Recommended Use:** Engineering thermoplastic stock shape

## Section 2: Hazard Identification

**GHS – Classifications** 

Classification: None

Signal Word: None

Pictograms and Symbols: None

Hazard Statements: None

Precautionary Statements: None

# Section 3: Composition/Information on Ingredients

This is a polymeric material. All constituents are encapsulated within the polymer system and therefore present minimal likelihood of exposure under normal conditions of processing and handling.

Chemical Name	CAS No.	Weight %
Polyphenylsulfone	25608-64-4	>98
Titanium dioxide	13463-67-7	0-5
Carbon black	1333-86-4	0-1

#### Section 4: First-Aid Measures

**Eyes:** Flush with plenty of water for at least 15 minutes. Seek medical attention if irritation continues.



**Skin:** No health risks concerning skin contact at room temperature. Wash with soap and water. If molten material comes in contact with the skin, cool under running water. Do not attempt to remove the molten material from the skin. Get medical attention immediately.

**Inhalation:** If fumes from overheating are inhaled, remove to fresh air. Seek medical attention if respiratory symptoms occur or breathing becomes difficult.

**Ingestion:** Rinse the victim's mouth with plenty of water. Do not induce vomiting. Seek medical attention.

## Section 5: Fire-Fighting Measures

Fire-fighters should protect themselves from decomposition and combustion products by using a fullface self-contained breathing apparatus and impervious protective clothing. Extinguish fires with water, foam, carbon dioxide or dry chemical media.

Hazardous gases/vapors produced in fire are: carbon monoxide; sulfur oxides, and hydrocarbons. The release of other hazardous decomposition products is possible.

Degredation under vacuum at 842° F may yield hydrogen sulfide. Pyrolysis under vacuum at 527° F may yield Dibenzothiophene.

Dust is flammable and explosive when finely divided and suspended in air.

## Section 6: Accidental Release Measures

If a spill occurs, stop the leak at the source and sweep up for disposal. Do not flush to sewers or waterways.

## Section 7: Handling and Storage

#### **Precautions for Safe Handling**

Personal hygiene such as washing the hands and face immediately after working with this material and before eating is recommended.

Dust may form explosive mixtures with air. Avoid dust formation and control ignition sources. Plastic dust particles suspended in air are combustible and may be explosive. Keep away from heat, sparks, flame, and other ignition sources. Prevent dust accumulations and dust clouds. Employ ground, bonding, venting, and explosive relief provisions in accordance with accepted engineering practices and NFPA provisions in any process capable of generating dust and/or static electricity. Explosion hazards apply only to dusts, not granular forms of this product. The handling of powder in both loading and unloading operations, as well as fabrication, may cause dust to be formed and necessary precautions for personal protection should be used. As with all finely divided materials precautions should be taken to avoid inhalation and eye contact.

If in dust form, transfer from storage with a minimum amount of dusting. Ground all transfer, blending, and dust collecting equipment to prevent static sparks in accordance with NFPA 70 "National Electric Code." Review and comply with all relevant NFPA provisions, including but not limited to NFPA 484 and NFPA 654 related to combustible dust hazards. Remove all ignition sources from material handling, transfer, and processing areas where dust may be present. Local exhaust ventilation should be provided in work area.

#### **Precautions for Safe Storage**



Store in a sprinkler protected warehouse. Since products are organic, they will burn with a hot flame if ignited. Avoid contact with ignition sources such as open flames. Keep a fire extinguisher near if welding is done in the area of organic products. If a heat source is present, keep the area well ventilated.

## Section 8: Exposure Controls/Personal Protection

Chemical Name	ACGIH TLV	OSHA PEL	NIOSH REL
Particulates	10 mg/m <sup>3</sup>	15 mg/m³ – Total	Not Determined
		5 mg/m <sup>3</sup> – Respirable	
Carbon Black	3.5 mg/m <sup>3</sup>	3.5 mg/m <sup>3</sup>	3.5 mg/m <sup>3</sup>

#### **Engineering Measures:**

Provide local exhaust ventilation to keep airborne particulate concentrations below 15 mg/m<sup>3</sup>, the OSHA limit for nuisance dusts.

#### **Personal Protective Equipment: Eyes/Face**

Safety glasses with side shields.

#### **Personal Protective Equipment: Skin**

When handling molten material, protective clothing such as long sleeves or laboratory coat should be worn. Use heat-resistant gloves, boots, and face protection.

#### **Personal Protective Equipment: Respiratory**

If levels are above published OELs, then a NIOSH approved respirator.

Good industrial hygiene practice should be followed which includes preventing eye contact, minimizing skin contact, and minimizing inhalation of dust, vapors or mist.

## **Section 9: Physical and Chemical Properties**

Appearance and Odor Odor Threshold Specific Gravity (Relative Density) Solubility in Water VOC Content (%) pH Melting Point/Freezing Point Vapor Pressure Vapor Density Evaporation Rate Boiling Point Flammability Flash Point Explosion Data Auto ignition Point Partition Coefficient: n-octanol/water Decomposition Temperature	Solid in rod or plate form with no odor No Information Available 1.29 Negligible <1% No data available 220° C / 428° F No data available No data available No data available No data available Combustible No data available LEL – No data available UEL – No data available No data available No data available
Decomposition Temperature	No data available
Viscosity	No data available

## Section 10: Stability and Reactivity



Reactivity:

None known

## Chemical Stability:

Material is stable under normal industrial conditions and is not susceptible to hazardous polymerization.

## **Conditions to Avoid:**

To avoid thermal decomposition, avoid elevated temperatures above 430° C / 806° F. Heating can result in the formation of gaseous decomposition products, some of which may be hazardous.

#### Incompatibility:

Polymeric resins

## Hazardous Decomposition Products:

At elevated temperatures Carbon oxides, Sulpher oxides, and hydrocarbons may occur. The release of other hazardous decomposition products is possible.

# Section 11: Toxicological Information

**Signs and Symptoms of Overexposure:** Eye irritation signs and symptoms may include a burning sensation, redness, swelling, and/or blurred vision. Skin irritation signs and symptoms may include a burning sensation, redness and swelling. Respiratory irritation signs and symptoms may include a temporary burning sensation of the nose and throat, coughing, and/or difficulty breathing.

#### Aggravated Medical: None.

Acute Effects: No data available. Skin Corrosion/Irritation: No data available. Serious Eye Damage/Irritation: No data available. Ingestion: No data available. Inhalation: No data available. Respiratory or Skin Sensitization: No data available.

Chronic Effects:

Germ Cell Mutagenicity: No data available. Carcinogenicity: IARC Group 2B (Titanium Dioxide) Reproductive Toxicity: No data available. STOT-single Exposure: No data available. STOT -multiple Exposure: No data available. Aspiration Hazard: No data available. Not expected to be an aspiration hazard.

Primary Route of Entry: Inhalation of particulates.

## Section 12: Ecological Information

# Ecotoxicity:

There aren't known ecological toxicity values.

#### Persistence and degradability:

It's expected high persistence and slow degradability.



#### **Bioaccumulative Potential:**

It's expected moderate to high bioaccumulative potential.

#### Mobility in Soil:

No data available

#### **Other Adverse Effects:**

No data available

Chemical Name	Toxicity to Algae	Toxicity to Fish	Microtox	Daphnia Magna (Water Flea)

## Section 13: Disposal Considerations

According to the 'European Waste Catalogue and Hazardous Waste List', uncontaminated waste from the products is not classified as hazardous. The following six-digit codes can be used:

- 07 02 13 waste plastic from the manufacture, formulation, supply and use of plastics
- 12 01 05 plastic shavings and turnings
- 16 01 19 plastic, from end-of-life vehicles from different means of transport (including off-road machinery) and wastes from dismantling of end-of-life vehicles and vehicle maintenance
- 17 02 03 plastic construction and demolition wastes
- 20 01 39 plastics from municipal wastes (household waste and similar commercial, industrial and institutional wastes)
- Waste disposal: When recycling is not feasible, waste disposal by incineration or landfill can be applied. Disposal methods shall conform to local or other government regulations.

## Section 14: Transportation Information

US Department of Transportation Classification (49CFR)

Not classified as hazardous for transport.

# Section 15: Regulatory Information

SARA Section 302 & 304: No chemicals

SARA Section 313:

The following component is subject to reporting levels established by SARA Title III, Section 313:

• None

TSCA:

All components of this product are either listed or are exempt on the TSCA inventory.

# Section 16: Other Information



## Label Information

**Product Identifier:** Sultron<sup>™</sup> LSG R5100 PPSU and Sultron<sup>™</sup> LSG R5500 PPSU natural and colors

Manufacturer:

Mitsubishi Chemical Advanced Materials, Inc. 2120 Fairmont Ave. Reading, PA 19605 (610) 320-6600

In case of an emergency, please call Chemtrec 1-800-424-9300.

Classification: None

Signal Word: None

Pictograms and Symbols: None

Hazard Statements: None

Precautionary Statements: None

The information set forth herein has been gathered from standard reference materials and/or supplier test data and is, to the best knowledge and belief of Mitsubishi Chemical Advanced Materials, Inc., accurate and reliable. Such information is offered solely for your consideration, investigation and verification, and it is not suggested or guaranteed that the hazard precautions or procedures mentioned are the only ones that exist Mitsubishi Chemical Advanced Materials, Inc. makes no warranties, expressed or implied, with respect to the use of such information or the use of the specific material identified herein in combination with any other material or process, and assumes no responsibility therefor.

Acetron<sup>™</sup>, Altron<sup>™</sup>, Armor-X<sup>™</sup>, BlOpreg<sup>™</sup>, Borotron<sup>™</sup>, carboNXT<sup>™</sup>, Ceram P<sup>™</sup>, Cestidur<sup>™</sup>, Chirulen<sup>™</sup>, Duratron<sup>™</sup>, Ertacetal<sup>™</sup>, Ertalon<sup>™</sup>, Ertalyte<sup>™</sup>, Extrulen<sup>™</sup>, Flextron<sup>™</sup>, Fluorosint<sup>™</sup>, Ketron<sup>™</sup>, Keylon<sup>™</sup>, Kyron<sup>™</sup>, KyronMAX<sup>™</sup>, KyronTEX<sup>™</sup>, MC<sup>™</sup>, Nylatrack<sup>™</sup>, Nylatron<sup>™</sup>, Proteus<sup>™</sup>, Quadrant<sup>™</sup>, QuickSilver<sup>™</sup>, RCH<sup>™</sup>, Sanalite<sup>™</sup>, Semitron<sup>™</sup>, Statera<sup>™</sup>, Sterra<sup>™</sup>, Sultron<sup>™</sup>, System TIVAR<sup>™</sup>, Techtron<sup>™</sup>, TIVAR<sup>™</sup>, and Ultraslide<sup>™</sup> are registered trademarks of the Mitsubishi Chemical Advanced Materials group of companies.

All statements, technical information, recommendations, and advice are for informational purposes only and are not intended and should not be construed as a warranty of any type or term of sale. The reader, however, is cautioned that Mitsubishi Chemical Advanced Materials does not guarantee the accuracy or completeness of this information and it is the customer's responsibility to test and assess the suitability of the products of Mitsubishi Chemical Advanced Materials in any given application or for use in a finished device.